Guangdong Taojiayue High-tech Material Technology Co., Ltd. Tel:+86-020-39009191 P/Skype/Whatsapp:+8618566530506 Email:info@linchemical.com Website:www.linchemical.com No.106, Feng Zhe East Road, Nansha Area, Guangzhou City China

LINANOX DSTP

Chemical name: Distearyl thiodipropionate

Formula	$C_{42}H_{82}O_4S$	
Molecular Weight	683	s - CII2 - CH2 - COOC IB II J2
CAS#	693-36-7	

Specification:

Appearance		White crystalline powder
Ash		Max.0.10%
Melting point		63.5-68.5℃
Solubility (20°C)	Water	< 0.1
	MeoH	< 0.01
	EtoH	< 0.01
	Acetone	U
	Ch2Cl2	S
	Hexane	S

Application: >DSTP is a good auxiliary antioxidant and is widely used in polypropylene, polyethylene, polyvinyl chloride, ABS and lubricating oil. It has high-melting and low- volatility .

>It can be used in combination with phenolic antioxidants and ultraviolet absorbers to produce synergistic effect.

Handing and safety:

>FDA approved 1998 for the manufacture of resinous/polymeric coatings in safe contact with food for articles for use in all stages of production, processing, packaging, and transport of food, 21CFR175.300.

The information and statement herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility, Users should undertake sufficient verification and testing to determine the suitable for their own particular purpose of any information or products referred to herein. No warranty of fitness for a particular purpose is made.

>For additional handing and toxicological information, please consult us for

Maternal Safety Date Sheet

Package: Packed with plastic bag in composite plastic woven sack, Net 25kg/bag,

or according to customers' requirements.

The information and statement herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility, Users should undertake sufficient verification and testing to determine the suitable for their own particular purpose of any information or products referred to herein. No warranty of fitness for a particular purpose is made.