LINSORB 384-2

Chemical Name:

95% Benzenepropanoic acid, 3-(2H-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy-, C7-9-branched and linear alkyl esters, and 5% 1-methoxy-2-propyl acetate

Formula	$C_{27}H_{37}N_3O_3$	+
Molecular Weight	451.6	N N O
CAS#	127519-17-9	©N Ö

Physical Properties:

Appearance	Light amber viscous liquid
specific gravity	1.07g/cm^3
Viscosity	2600-3600mPas(20 °C)
Purity	≥93%(HPLC)
Transmittance	460nm≥95%
Transmittance	500 nm>97%

Applications:

- > Linsorb 384-2 has good thermal stability and compatibility with various polymers and can be used in automotive coatings and general industrial coatings, such as coil coatings, wood coatings.
- > LINSORB-384-2 can be used together with hindered amine light stabilizers, such as LINSORB-292 or LINSORB-123. Synergistic effects between these additives provide better inhibition of yellowing, cracking, blistering, shedding and matting of coatings.

Handing and safety:

>For additional handing and toxicological information, please consult us for Maternal Safety Date Sheet

Package:

20/25/200KG plastic drum