

LINSORB 783

Chemical Name:

Formula	50%LINSORB 944+50%LINSORB 622
Molecular Weight	2000-3100

Physical Properties:

Appearance	white to slightly yellow pastilles
Softening point	55°C-140°C
Flash point	192°C

Applications:

>Synergistic mixture of oligomeric hindered amine stabilizers

>LINSORB 783 is particularly well suited for LDPE,LLDPE, HDPE films, tapes and thick sections and for PP films. It is also the product of choice for thick sections where indirect food contact approval is required.

>It's concentrations range between 0.1 % and 1.5 %, depending on the substrate, processing conditions and application

Handling and safety:

>In accordance with good industrial practice, handle with care and avoid unnecessary personal contact. Avoid continuous or repetitive breathing of dust. Use only with adequate ventilation. Avoid dust formation and ignition sources

>For additional handling and toxicological information, please consult us for Maternal Safety Date Sheet

Package:

25kg per fiber drum, 9*3 layer 27drum per pallet, or according to requirements.